



Since 1990

# DECCOBOND 101

## Lamination Glue

**DESCRIPTION:** *DECCOBOND 101* is a polymer based emulsion adhesive formulated for fast setting, good bond strength and is free from any solvents.

**APPLICATION:**

*DECCOBOND 101* is designed for laminating and overlaying of arborite, veneers or melamine laminates onto fibreboards, medium density boards, solid lumber or any wood work.

*DECCOBOND 101* can also be used to glue paper, fabric and wood.

**PREPARATION & USAGE:**

*DECCOBOND 101* is supplied ready to use and do not require mixing. Surfaces to be glued must be clean and free from dust, grease or oils. If natural wood oil is present in some species of wood, clean it with alcohol rub or with solvent and allow the surface to dry before gluing takes place to ensure better bonding.

**Assembly time:**

The assembly time varies and is dependent on the species of wood and moisture content. It is also affected by the room temperature, relative humidity, glue spread, etc. and can be determined by regular use.

**Open assembly time:**

8 degree C	30 to 35 min
15 degree C	15 to 20 min
20 degree C	10 to 15 min

Maximum assembly time can best be determined by a particular application and actual conditions.

**Pressure:**

Excessive pressure on smooth surfaces may staved glue lines. Similarly, high pressure on

hard wood may also starve glue lines if insufficient spread is provided.

**CLEAN UP:**

Brushes, rollers, glue guns & spreaders can be easily cleaned with water & sponge. Warm water cleans better. To prevent damage, keep application equipment in water after use for easier cleaning.

**STORAGE:**

*DECCOBOND 101* is stable. Stores well for at least 9 to 12 months at room temperature of 20° C. Do not store next to heaters or very high temperatures of 65° C or more. *DECCOBOND 101* is packed in plastic or polyethylene containers. Do not store in unlined metal containers as there will be reactions between the adhesive and the unlined container resulting in dark stains and contaminants. **KEEP FROM FREEZING.**

**LEED Credit:**

*DECCOBOND 101* may contribute to LEED certification projects based on the following categories.

LEED CREDIT	
LEED (Version 3.0)	LEED Point
Regional Materials (MR Credit 5.0)	2
Low-Emitting Materials (IEQ Credit 4.1)	1

**VOC Compliant:**

SCAQMD Rule #1168 (South Coast Air Quality Management District)



**PHYSICAL PROPERTIES**

<b>Type</b>	White emulsion	<b>Viscosity</b>	2,500 – 3,200 cps
<b>Appearance</b>	White	<b>Odor</b>	Mild to None
<b>Solids</b>	47 - 48 %	<b>Flammability</b>	Non-flammable
<b>Specific Gravity</b>	1.08	<b>VOC</b>	1.1 g/L

**PACKING INFORMATION**

Size	Pail/Pallet
5 gallon pail	36
55 gallon drum	-
275 gallon tote	-



**TENCO WESTECH POLYMERS INC.**  
160-6333 Graybar Road, Richmond, B.C.  
Canada V6W 0C4 t 604-276-8538

The above data are the results of carefully executed investigation. We do not guarantee the applicability of this information or suitability of our products in any given situation, because we cannot control the wide range of possibility. The products discussed are sold without warranty, either express or implied. User and/or Buyer assume all risks and liability for the results obtained whether used singly or in combination with other products. Our liability for all damages hereunder shall in no case exceed the purchase price of the quantity consumed of the particular shipment with respect to which such damages may be claimed.