



Since 1990

DECCOSEAL 506

Waterproofing Barrier Coat

DESCRIPTION:

DECCOSEAL 506 Waterproofing Barrier Coat is a cold-applied, single-component, hydrophobic hybrid-polymer, and waterproofing compound. It does not shrink. It is solvent free, LEED® and volatile organic compound (VOC) compliant, and has very low odor. It will not crack in extreme cold. It dries clear and cured film can withstand hydrostatic pressure of 10 lbs of more. It is ideal for waterproofing barrier in glue-down wood flooring and suitable for in-floor hot water radiant heated subfloor with adhesive applications.

APPLICATION:

DECCOSEAL 506 Waterproofing Barrier Coat can be used on interior or exterior surfaces, such as but not limited to concrete, masonry, metal, and wood surfaces where protection from water intrusion is desired. The product can be used for both above-grade and below-grade applications. It is also suitable for both horizontal and vertical surfaces.

Directions:

Surface Preparation

Surfaces must be clean, dry and smooth, free of coating, loose materials, projections, oil, old adhesive, wax, sealers or other contaminants. DO NOT USE petroleum solvents such as mineral spirits or xylene. Physical removal such as power washing is acceptable. In cold temperature, the surface must be free of frost. Do not use asphalt-based primers on concrete or metal surfaces.

Application Method

Make sure product is at room temperature (store at room temperature for 24 hours) before application to ensure ease of application. Apply by brush, squeegee or roller. If a second coat is necessary, apply as soon as possible, but no more than eight hours apart.

Superior Quality. Revolutionary.

- **Strong & Resilient**
- **Ultimate Bond Strength**
- **Moisture Barrier & Waterproof**
- **Easy to Roll on**
- **Commercial-Grade**
- **Odor, VOC & Isocyanates Free**
- **High Solids**
- **Anti-microbial & Anti-fracture Membrane**
- **Interior & Exterior**

Applications

- **Vinyl Sheet**
- **Vinyl Plank/Tile/VCT**
- **Rubber Tile**
- **Vinyl Backed Carpet**

* Trademark of Tenco Westech Polymers Inc.

Clean Up:

Brush, squeeze, roller, and equipment can be easily cleaned with warm water while compound is still wet. Cured compound needs to be removed by mechanical means.

Dry Time:

DECCOSEAL 506 features a fast drying time. Recommended minimum application temperature is 12° C & above. Keep out traffic until coating is fully cured, light foot traffic in about 12 hours, normal traffic after 24 hours.

Actual drying time is temperature, humidity and wind dependent.

VOC Compliant:

Zero grams/liter SCAQMD Rule #1168 (South Coast Air Quality Management District)



LEED Credit:

DECCOSEAL 506 may contribute to LEED certification projects based on the following categories.

LEED CREDIT

LEED (Version 3.0)	LEED Point
Regional Materials (MR Credit 5.0)	2
Low-Emitting Materials (IEQ Credit 4.1)	1

COVERAGE

Waterproofing Barrier Coat	60 ft ² /gal (30 mils dry film thickness)
Surface texture & porosity will determine the final coverage rates.	

PHYSICAL PROPERTIES

Type	Hybrid Polymer	Odor	Mild to None
Appearance	White Emulsion	Flammability	Non-flammable
Solids	> 80%	VOC	complaint

STORAGE:

DECCOSEAL 506 is stable. Product is stable. Stores well at 8° - 20° C room temperature for at least 12 months from date of manufacture in unopened containers. **KEEP FROM FREEZING.**

PACKING INFORMATION

Size	Pail/Pallet
5 gallon pail	36
55 gallon drum	-
275 gallon tote	-



TENCO WESTECH POLYMERS INC.
160-6333 Graybar Road, Richmond, B.C.
Canada V6W 0C4 t 604-276-8538

The above data are the results of carefully executed investigation. We do not guaranteed the applicability of this information or suitability of our products in any given situation, because we cannot control the wide range of possibility. The products discussed are sold without warranty, either express or implied. User and/or Buyer assume all risks and liability for the results obtained whether used singly or in combination with other products. Our liability for all damages hereunder shall in no case exceed the purchase price of the quantity consumed of the particular shipment with respect to which such damages may be claimed.